

TECWOOL[®] MORTAR

www.mercortecresa.com

TECWOOL[®] T

TECHNICAL CHARACTERISTICS AND SPECIFICATIONS

| | |
|------------------------------|---------------------------------|
| Composition | Cement, rock wool and additives |
| Fire reaction | A1 |
| Bulk mortar density | 175 Kg/m ³ ± 10% |
| Thermal conductivity | 0,0456 W/mk |
| Alkalinity (pH value) | 12,5 |
| Resistance to fungi | Immune |
| Adherence | 0,014 N/mm ² failure |
| Marketing | 15 kg sacks in 450 kg pallets |