

TECFILL®

TECHNICAL CHARACTERISTICS

Nominal Density	80 Kg/m ³ ± 10%
Thermal Conductivity	0,038 W/m.K
Fire reaction	A1
Melting Point	≥ 1350 °C
Biological Behaviour	Not affected by microorganisms. Rot-proof. Chemically neutral.

THERMAL RESISTANCE

Thickness (mm)	R (m ² K/W)
30	0,79
40	1,05
50	1,31
60	1,57
70	1,84
80	2,1
90	2,36
100	2,63
110	2,89
120	3,15
130	3,42
140	3,68
150	3,94
160	4,21
170	4,47
180	4,73
190	5
200	5,26